

Requested Patent: EP0992539A1

Title:

ETHYLENE (CO)POLYMERS, AND LAMINATE AND HOLLOW MOLDING MADE BY USING THE SAME ;

Abstracted Patent: EP0992539 ;

Publication Date: 2000-04-12 ;

Inventor(s):

TABUCHI DAIZO (JP); TAKAHASHI KEI (JP); KONDOU HARUHIKO (JP); OGAWA KOICHI (JP); KANAZAWA SATOSHI (JP) ;

Applicant(s): JAPAN POLYOLEFINS CO LTD (JP) ;

Application Number: EP19980928624 19980623 ;

Priority Number(s):

WO1998JP02784 19980623; JP19970166936 19970624; JP19970166937 19970624 ;

IPC Classification: C08F10/02; B32B27/32 ;

Equivalents: CN1105119B, WO9858999 ;

ABSTRACT:

Ethylene (co)polymers each having specified values of (1) density, (2) molecular weight distribution (Mw/Mn), (3) relationship between die swell (DS) and shear rate (γ) in a region of shear rate (γ), (4) relationship between stress (σ) and maximum stress (σ_{max}) in a stress-strain curve in uniaxial stretching, (5) the ratio of sample diameter to initial sample diameter and the time for sample breakage during uniaxial stretching under a constant tension, laminates and hollow moldings made by using the same. The ethylene (co)polymers are excellent in drawdown resistance, puncture resistance, parison control response, pinch-off properties, durability, and fire resistance.



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 992 539 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:
12.04.2000 Bulletin 2000/15

(51) Int. Cl.⁷: C08L 23/04, C08F 10/02,
B32B 27/32

(21) Application number: 98928624.0

(86) International application number:
PCT/JP98/02784

(22) Date of filing: 23.06.1998

(87) International publication number:
WO 98/58999 (30.12.1998 Gazette 1998/52)

(84) Designated Contracting States:
BE DE ES FR GB IT

(30) Priority: 24.06.1997 JP 16693697
24.06.1997 JP 16693797

(71) Applicant:
Japan Polyolefins Co., Ltd.
Tokyo, 105-0001 (JP)

(72) Inventors:
• OGAWA, Koichi,
Japan Polyolefins Co., Ltd.
Kawas.-ku, Kawas.-shi, Kanagawa 210-0863 (JP)
• KONDOU, Haruhiko,
Japan Polyolefins Co., Ltd.
Ohita-shi, Ohita 870-0111 (JP)


• TAKAHASHI, Kei,
Japan Polyolefins Co., Ltd.
Ohita-shi, Ohita 870-0111 (JP)
• TABUCHI, Daizo,
Japan Polyolefins Co., Ltd.
Kawas.-ku, Kawas.-shi, Kanagawa 210-0863 (JP)
• KANAZAWA, Satoshi,
Japan Polyolefins Co., Ltd.
Kawas.-ku, Kawas.-shi, Kanagawa 210-0863 (JP)

(74) Representative:
Harvey, David Gareth et al
Graham Watt & Co.
Riverhead
Sevenoaks Kent TN13 2BN (GB)

(54) ETHYLENE (CO)POLYMERS, AND LAMINATE AND HOLLOW MOLDING MADE BY USING THE SAME

(57) Ethylene (co)polymers each having specified values of (1) density, (2) molecular weight distribution (Mw/Mn), (3) relationship between die swell (DS) and shear rate ($\dot{\gamma}$) in a region of shear rate ($\dot{\gamma}$), (4) relationship between stress (σ) and maximum stress (σ_{max}) in a stress-strain curve in uniaxial stretching, (5) the ratio of sample diameter to initial sample diameter and the time for sample breakage during uniaxial stretching under a constant tension, laminates and hollow moldings made by using the same. The ethylene (co)polymers are excellent in drawdown resistance, puncture resistance, parison control response, pinch-off properties, durability, and fire resistance.

Fig. 1



(a)

Description

TECHNICAL FIELD

5 [0001] This invention relates to a novel ethylene (co)polymer, and laminate and hollow molding or blow molded products made by using the same. More particularly, this invention relates to an ethylene (co)polymer which is excellent in mechanical strengths such as impact resistance, moldability, etc. and applicable to extrusion molding, injection molding, blow molding, etc., which is excellent for use in large blow molded products required of drawdown resistance, puncture resistance, parison thickness controllability (parison control response), pinch-off properties, durability, etc., in particular excellent in fire resistance required for fuel tanks, to hollow moldings, laminates and hollow multilayer moldings made by using the same.

BACKGROUND ART

15 [0002] Generally, detergent bottles, food containers such as beverage bottles and vegetable oil bottles, large vessels such as drum cans and industrial cans, fuel containers such as kerosene cans and gasoline tanks, spoilers, bumpers and the like are produced by a blow molding process. The blow molding process is to pinch with a mold a cylindrically extruded parison composed of a melted resin, blowing air into the parison to blow up and change the shape of it so as to conform to the shape of the cavity of the mold, and then cooling it.

20 [0003] The blow molding process is widely utilized since it is applicable widely to large fuel tanks having complicated shapes, drums, and further panel-like moldings as well as hollow moldings such as bottles and since molding is simple and molding costs covering molds are inexpensive.

[0004] Recently, in the field of large vessels such as drum cans and large containers, substitution by plastics is being carried forward positively taking into consideration freedom in shape, economy, safety, and adaptability to environmental problems.

25 [0005] It is also the case in the field of automobile industry such as fuel tanks, bumpers and spoilers. Particularly in the field of fuel tanks, substitution by plastics proceeds remarkably along with the development of fuel permeation preventing technology by a co-extrusion technology, a sealer technology, a continuous multi-ply technology, etc.

30 [0006] When large products are blow molded, a phenomenon that a parison droops down due to its own weight (drawdown) tends to occur. To make the drawdown small, it has been known to use a resin having sufficiently high viscosity and melt tension.

[0007] In molding hollow moldings having a complicated shape, there tends to occur a local increase in blow ratio to cause puncture or local thinning of a parison. To prevent the puncture or local thinning of a parison, it has been known to control the thickness of the parison (parison control) to make a desired portion thick or make alterations in the appearance such as alteration of the shape of a mold.

35 [0008] Conventionally, there has been a problem that an increase in molecular weight and an increase in viscosity in order to improve the drawdown resistance of polyethylene results in aggravation of extrusion properties (extrusion rate, parison surface conditions) and welded strength of a parison becomes worse so that the pinch-off shape is worsened. As a method for solving the problem have been known, for example, the method in which a multi-step polymerization method using a Ziegler-type catalyst (Japanese Patent Application Laid-open No. Sho 55-152735), the method

40 in which a small amount of radical generator and crosslinking auxiliary are added to polyethylene resin (Japanese Patent Publication Hei 2-52654), the method in which two polyethylene components are blended in a certain proportion (Japanese Patent Application Laid-open No. Hei 6-299009), etc.

[0009] However, recently larger and more complicated blow moldings are being produced so that further improvement of drawdown resistance of a resin is becoming necessary in order to extrude a heavy parison to a larger length in a stable manner. Also, in order to improve the fuel permeation of a fuel tank, there is a demand for a multilayer fuel tank provided with an ethylene/vinyl acetate copolymer saponification product (hereafter, called EVOH), which has poor heat resistance, as a barrier material. In molding them, a blow molding machine of a continuous extrusion type having a smaller retention portion and suffering less thermal decomposition of EVOH is becoming to be put in use for blow molding larger fuel tanks in place of a blow molding machine of an accumulator type which has heretofore been used for larger size molding. As compared with the accumulator type, the continuous extrusion type molding machine takes a long time for extruding a parison so that drawdown of a parison tends to occur more frequently. Therefore, there is a demand for a resin having an increased drawdown resistance.

45 [0010] For this purpose, the improved polyethylenes obtained, for example, by the above-mentioned processes are insufficient in drawdown resistance for obtaining large hollow moldings.

55 [0011] Also, according as the shape of hollow moldings becomes more complicated, there come into question phenomena that parisons will puncture when they are being formed by blowing and that local thinning of a product will occur at its corner portions, etc.

[0012] To prevent these problems, a method has generally been used in which a parison controller is used in order to control the thickness of a parison. However, conventional polyethylene and resin compositions thereof grow to have insufficient parison thickness controllability (parison control response) so that improvement of parison control response is desired. Also, as the method for enabling molding of deep drawn articles having complicated shapes, there have been known, for example, the method in which a split mold is used (Plastics, Vol. 42, No. 5, p.64-71) and the method in which a blow molding machine with a mold slanting mechanism is used (Plastics, Vol. 41, No. 10, p.59-69). However, the above-mentioned methods have a problem that costs for the apparatus and mold are high.

[0013] Furthermore, in the field of fuel tanks, which require fire resistance as one of the requisite properties, there have been proposed ethylene copolymers having an α -olefin content within a specified range and inherent viscosity, zero shear viscosity and time for melt stretching breakage being prescribed to be within respective specified ranges as a preferred material (Japanese Patent Application Laid-open No. Hei 7-101433). However, they are in an insufficient state in molding processability and fire resistance to cope with weight reduction and thickness reduction.

DISCLOSURE OF THE INVENTION

[0014] An object of the present invention is to overcome the defects of conventional polyethylenes and provide an ethylene (co)polymer having excellent drawdown resistance, puncture resistance, parison control response, and pinch-off properties.

[0015] Another object of the present invention is to provide blow molded products which are improved against the phenomena that the parison of blow molding having a complicated shape will puncture when expansion shaped and that there will occur local thinning of corner portions of products, by use of the above-mentioned ethylene (co)polymer or its composition.

[0016] Still another object of the present invention is to provide blow molded multilayer containers having a capability of preventing permeation of various fuels and causing no local thinning.

[0017] In a first aspect, the present invention relates to an ethylene (co)polymer which satisfies the following requirements (a) to (d):

- (a) a density of 0.93 to 0.98 g/cm³,
- (b) a molecular weight distribution (Mw/Mn) of 25 to 50,
- (c) that values of slope a and of intercept b obtained from a die swell (DS) and a shear rate ($\dot{\gamma}$) measured in a region of shear rate ($\dot{\gamma}$) (6.08 to 24.8 sec⁻¹) at 230 °C, in accordance with the equation (1) below

$$DS = a \times \ln(\dot{\gamma}) + b \quad (1)$$

are such that $a \leq 0.05$ and $b \leq 1.45$,

- (d) that the stress ratio of a stress (σ) at a strain of 1.0 to a maximum stress (σ_{max}) in a stress-strain curve for uniaxial stretching at 0.1 sec⁻¹ measured at 170 °C is such that $\sigma_{max}/\sigma \geq 2.1$.

Preferably, the present invention relates to an ethylene (co)polymer which further satisfies the requirement

- (e) that a value of (α) as defined by the equation (2) below

$$\alpha = \epsilon/t \quad (2)$$

(wherein α is ϵ/t when ϵ defined by $\epsilon = -\ln(\text{sample diameter after } t \text{ seconds } l_t / \text{initial sample diameter } l_0)$ is 0.6) when uniaxially stretched under a constant tension such that initial stress (= tension/initial cross section of sample) measured at 170 °C is 3.0×10^4 Pa is not greater than 0.03 and time for sample breakage is not shorter than 25 seconds.

More preferably, the present invention relates to an ethylene (co)polymer which further satisfies the requirement

- (f) HLMFR ≤ 10 g/10min and which has a C₃₋₂₀ α -olefin content of 10 mol% or less.

[0018] In a second aspect, the present invention relates to blow molded products comprising the above-mentioned ethylene (co)polymer or composition thereof, preferably a fuel tank which exhibits superiority of the above-mentioned ethylene (co)polymer or composition thereof.

[0019] In a third aspect, the present invention relates to a laminate comprising a layer comprising the above-mentioned ethylene (co)polymer or composition thereof, a barrier layer, and optionally an adhesive layer and preferably to a laminate in which the barrier layer comprises at least one member selected from polyamide resins, ethylene/vinyl acetate copolymer saponification products, polyester resins, polyvinylidene chloride resins and compositions thereof. It is desirable that for the adhesive layer, adhesive resins which comprise copolymers of unsaturated carboxylic acids or

derivatives thereof with olefins or polyolefin resins modified with unsaturated carboxylic acids or derivatives thereof be used.

[0020] In a fourth aspect, the present invention relates to a blow molded multilayer container comprising a laminate which comprises a layer comprising the above-mentioned ethylene (co)polymer or compositions thereof, an adhesive layer and a barrier layer, and preferably such exhibits superiority in multilayer blow molded fuel tanks.

5 [0021] In a fifth aspect, the present invention relates to a blow molded multilayer container comprising a laminate which comprises at least one resin layer selected from the recycled resin composed of the above-mentioned laminate, or compositions of the ethylene (co)polymer according to the first aspect containing the recycled resin, or compositions of these with polyolefin resin, a barrier layer, and optionally an adhesive layer, and preferably such exhibits superiority in physical properties and economy in blow molded multilayer fuel tanks.

BRIEF DESCRIPTION OF THE DRAWINGS

[0022]

15 Fig. 1 is diagrams illustrating pinch-off properties when blow molding ethylene (co)polymers (2) of example and comparative example using a mold (1), with (a) being a vertically cut cross sectional view with respect to the pinch-off line of blow molding, (b) and (c) being partial enlarged views of (a) at a pinch-off middle portion (M), with (b) showing that the pinch-off shape is in a good state and (c) showing that the pinch-off shape is in a bad state.

DETAILED DESCRIPTION OF THE INVENTION

[0023] Hereafter, the present invention will be described in more detail.

25 [0024] The present invention has been achieved based on the finding that ethylene (co)polymer comprising an ethylene homopolymer or a copolymer of ethylene and α -olefin having 3 or more carbon atoms and having a density, a molecular weight distribution, a relationship between a die swell (DS) and a shear rate ($\dot{\gamma}$), a stress ratio, a time for melt breakage of resin which are adjusted to specified ranges is excellent in drawdown resistance, puncture resistance, parison control response, pinch-off shape properties, fire resistance, etc.

30 [0025] The ethylene (co)polymer of the present invention is an ethylene homopolymer or a copolymer of ethylene with an α -olefin having 3 to 20 carbon atoms. The α -olefin include, for example, propylene, 1-butene, 1-pentene, 1-hexene, 4-methylpentene-1, 1-octene, 1-decene, etc. The content of α -olefin is 10 mol% or less. If the content of α -olefin exceeds 10 mol%, there is the fear that the rigidity of (co)polymer decreases.

[0026] The ethylene (co)polymer of the present invention has a density of 0.93 to 0.98 g/cm³, and preferably 0.944 to 0.97 g/cm³. If the density is below 0.93 g/cm³, the rigidity and fire resistance decrease. On the other hand, if the density exceeds 0.98 g/cm³, the impact strength decreases.

35 [0027] The ethylene (co)polymer of the present invention has a molecular weight distribution (Mw/Mn) which must be in the range of 25 to 50, preferably 27 to 50, and more preferably 30 to 50.

[0028] If the molecular weight distribution is below 25, drawdown resistance and extrusion properties are poor while a molecular weight distribution exceeding 50 results in an increased die swell (DS) and an increased slope (a) of the equation (1) described below, a decreased parison control response, and an increased smoke when extruding parisons.

40 [0029] The ethylene (co)polymer of the present invention requires that values of slope a and of intercept b obtained from a die swell (DS) and a shear rate ($\dot{\gamma}$) measured in a region of shear rate ($\dot{\gamma}$) (6.08 to 24.8 sec⁻¹) at 230 °C, in accordance with the equation (1) below

$$45 \quad DS = a \times \ln(\dot{\gamma}) + b \quad (1)$$

(wherein $\ln(\dot{\gamma})$ is a natural logarithmic value of shear rate ($\dot{\gamma}$)) are such that $a \leq 0.05$ and $b \leq 1.45$. The value of slope a is preferably in the range of $a \leq 0.03$, and the value of intercept b is preferably in the range of $b \leq 1.35$.

50 [0030] Where the value of slope a is $a \leq 0.05$ and the value of intercept b is $b > 1.45$, or the value of slope a is $a > 0.05$, control of the thickness of a parison (parison control response) becomes difficult.

[0031] The ethylene (co)polymer of the present invention requires that the stress ratio of a stress (σ) at a strain of 1.0 to a maximum stress (σ_{max}) in a stress-strain curve in uniaxial stretching at 0.1 sec⁻¹ measured at 170 °C is in the range of $\sigma_{max}/\sigma \geq 2.1$, and preferably 2.5 or more. Where the stress ratio (σ_{max}/σ) is less than 2.1, the puncture resistance decreases.

55 [0032] More preferably, the ethylene (co)polymer of the present invention requires that a value of (α) as defined by the equation (2) below

$$\alpha = \epsilon/t$$

(wherein α is ϵ/t when ϵ defined by $\epsilon = -\ln(\text{sample diameter after } t \text{ seconds } l_t / \text{initial sample diameter } l_0)$ is 0.6) when uniaxially stretched under a constant tension such that initial stress (= tension/initial cross section of sample) measured at 170 °C is 3.0×10^4 Pa is not greater than 0.03 and time for sample breakage is not shorter than 25 seconds. If α exceeds 0.03, the deformation speed is higher whereas time for breakage less than 25 seconds results in a shortened hole opening time, so that there is the fear that fire resistance will be poor.

[0033] The ethylene (co)polymer of the present invention desirably has (f) HLMFR (High Load Melt Flow Rate) of 10.0 g/10 min or less. In particular, HLMFR for large blow molded products such as fuel tanks is preferably 5.0 (g/10 min) or less, and more preferably 4.0 (g/10 min) or less. Where HLMFR is above 10.0 (g/10 min), there is the fear that the drawdown resistance will remain unimproved.

[0034] The ethylene (co)polymer of the present invention is excellent in molding processability, rigidity and mechanical properties and is applied to extrusion molding, injection molding, blow molding, etc. Satisfaction of the above-mentioned requirements (a) to (e), and further the requirement (f) in the case of large or complicated-configured moldings such as tanks, overcomes the defects that the conventional polyethylene for blow molding has and provides the moldings with superiority in drawdown resistance, puncture resistance, parison control response, pinch-off properties or fire resistance.

[0035] The method for producing the ethylene (co)polymer of the present invention is not limited particularly so long as the requirements (a) to (d) above, desirably further the requirement (e), and more desirably further the requirement (f), are satisfied and it can be produced by a gas phase polymerization method, a slurry polymerization method, a solution polymerization method, etc., in the presence of a catalyst such as a Ziegler type catalyst, a Phillips type catalyst, a metallocene type catalyst or the like. Polymerization conditions are not limited particularly, but the polymerization temperature is usually 15 to 350 °C, preferably 20 to 200 °C, and more preferably 50 to 120 °C. The polymerization pressure is usually from atmospheric to 70 KgG/cm², preferably atmospheric to 50 KgG/cm² in the case of low/medium pressure methods, whereas in the case of high pressure methods, it is desirable that the polymerization pressure is usually not higher than 1,500 KgG/cm². The polymerization method may be one step polymerization or multi-step polymerization having two-steps or more in which different polymerization conditions such as hydrogen concentration, monomer concentration, polymerization pressure, polymerization temperature, catalyst, etc. are used and is not limited particularly. It is also possible to blend a plurality of components having different properties to prepare the ethylene (co)polymer of the present invention.

[0036] In the present invention, known additives such as antistatic agents, antioxidants, lubricants, anti-blocking agents, anti-fogging agents, organic or inorganic pigments, fillers, ultraviolet absorbents, dispersants, weathering agents, crosslinking agents, foaming agents, flame retardants, etc. can if desired be added in such amounts that the object is not obstructed.

[0037] The hollow moldings of the present invention are hollow molding made of the above-mentioned ethylene (co)polymer or composition thereof and include detergent bottles, food containers such as beverage bottles and vegetable oil bottles, vessels such as kerosene cans, drums and medicine bottles, various fuel containers, various components such as spoilers, bumpers, etc., housings of home electric products, OA apparatus. etc., panel-like construction components for constituting simple toilets, pallets and the like.

[0038] The above-mentioned ethylene (co)polymer or composition thereof may be blended with in addition to the ethylene (co)polymer of the present invention other polyolefin resin in amounts of 1 to 70% by weight. The method of producing hollow moldings of the present invention includes an extrusion blow molding method, an injection blow molding method, an extrusion stretching blow molding method, an injection stretching blow molding method, etc., but not limited particularly to a cold parison method, a hot parison method, etc.

[0039] In another aspect, the present invention relates to a laminate, comprising at least a layer comprising the above-mentioned ethylene (co)polymer or composition thereof (hereafter, referred to as the present resin layer), and a barrier layer. The above-mentioned laminate is not limited particularly so long as there is a structure of the above-mentioned two types of layers and the order of their lamination is not limited particularly. Generally, it is preferred that the barrier layer is an intermediate layer and along with (an) adhesive layer(s) an inner layer and/or outer layer is constituted by the present resin layer, and the outer or inner layer is an other polyolefin layer.

[0040] The barrier layer used in the present invention is constituted by at least one resin selected from polyamide resins, ethylene/vinyl acetate copolymer saponification products, polyacrylonitrile resins, polymethacrylonitrile resins, polyacetal resins, polyester resins, polyvinylidene chloride resins, polycarbonate resins, or compositions thereof. From the viewpoint of performance and physical properties, polyamide resins and polyvinylidene chloride resins are desirable.

[0041] The polyamide resins include polyamides obtained by polycondensation of a diamine with a dicarboxylic acid, polyamides obtained by condensation with an aminocarboxylic acid, polyamides obtained from a lactam, or copolymerized polyamides therefrom and those having a relative viscosity in the range of 1 to 6, a melting point of 170 to

280 °C, preferably 200 to 240 °C are used. More specifically, there can be cited nylon-6, nylon-66, nylon-610, nylon-9, nylon-11, nylon-12, nylon-6/66, nylon-66/610, nylon-6/11 and mixtures or polymer alloys of these polyamide resins with polyolefin resins and the like. Of these, nylon-6 is preferred.

[0042] The above-mentioned ethylene/vinyl acetate copolymer saponification products include, for example, ethylene/vinyl acetate saponification products such as an ethylene/vinyl acetate copolymer having a degree of saponification of 90% or more, preferably 95% or more and an ethylene content of 15 to 50 mol%.

[0043] The poly(meth)acrylonitrile resins are (co)polymers which are polymers composed of a methacrylonitrile unit and/or acrylonitrile unit or copolymers composed of these units and an alkyl (meth)acrylate unit, with the ratio by weight being in the range of 95:5 to 70:30, and which have a weight average molecular weight measured by a GPC method in the range of 60,000 to 200,000.

[0044] The above-mentioned polyester resins include thermoplastic polyesters such as polyethylene terephthalate, polybutylene terephthalate, polyethylene terephthalate/isophthalate, polyethylene naphthalate, and benzoic acid polyester and mixtures or polymer alloys of these with polyolefins.

[0045] The above-mentioned polyvinylidene chloride resins are polymers having a vinylidene chloride unit content of, for example, 70 to 99 mol%, and preferably 80 to 98 mol% and examples of comonomer of the polyvinylidene chloride resin include acrylic monomers such as acrylonitrile, methacrylonitrile, methyl methacrylate, ethyl methacrylate, propyl methacrylate, glycidyl methacrylate, glycidyl acrylate, hydroxyethyl acrylate, and hydroxypropyl acrylate, and vinyl monomers such as vinyl chloride.

[0046] The adhesive layer used in the present invention is constituted by a resin which is at least one adhesive resin selected from copolymers of an unsaturated carboxylic acid or derivatives thereof and an olefin, modified polyolefins having an unsaturated carboxylic acid or derivatives thereof grafted thereto or resin composition which is a mixture of that adhesive resin with unmodified polyolefin or the like.

[0047] Specific examples of the above-mentioned copolymers of unsaturated carboxylic acid or derivative thereof and an olefin include binary or more copolymers such as ethylene/(meth)acrylic acid copolymers, ethylene/glycidyl (meth)acrylate copolymers, ethylene/glycidyl (meth)acrylate/vinyl acetate terpolymers, ethylene/maleic anhydride copolymers, ethylene/(meth)acrylic acid/maleic anhydride terpolymers, styrene/maleic anhydride copolymers, and ethylene/styrene/maleic anhydride terpolymers.

[0048] The polyolefin modified with an unsaturated carboxylic acid or derivatives thereof of the present invention are polymers obtained by graft modifying polyolefin with an unsaturated carboxylic acid or derivatives thereof in the presence of a free radical generator such as an organic peroxide in an extruder or a kneader such as a Henschel mixer, or in a solvent such as a hydrocarbon.

[0049] Specific examples of the modified polyolefin include maleic anhydride-modified high density polyethylene, maleic anhydride-modified linear low density polyethylene, maleic anhydride-modified very-low density polyethylene, maleic anhydride-modified polypropylene and the like.

[0050] These are used singly or as modified polyolefin compositions by blending them with the above-mentioned unmodified polyolefin and optionally rubbers, etc., if desired.

[0051] The blending proportion of the adhesive resin and unmodified polyolefin is not limited particularly but generally the unmodified polyolefin may be blended in a blending proportion of 1 to 99% by weight. Further, it is desirable that the content of unsaturated carboxylic acid or derivatives thereof in the adhesive resin or composition thereof be selected in the range of 10^{-8} to 10^{-3} mole, and preferably 10^{-7} to 10^{-4} mole, per g of the resin component. With a content of below 10^{-8} mole, the adhesive strength is insufficient but a content exceeding 10^{-3} mole would cause "burn marks" or "gel" and be uneconomical.

[0052] The above-mentioned polyolefin resins include high/medium density polyethylenes, linear low density polyethylene, very-low density polyethylene, low density polyethylene by high pressure radical polymerization, ethylene/vinyl ester copolymers such as ethylene/vinyl acetate copolymers, polyethylene resins such as ethylene/unsaturated carboxylic acid alkyl ester copolymers such as ethylene/ethyl (meth)acrylate copolymers, propylene homopolymers, propylene/ α -olefin random or block copolymers, α -olefin homopolymers such as 1-butene polymers, etc., mutual copolymers of these or the like. Of these, high/medium density polyethylenes, linear low density polyethylene, very-low density polyethylene, etc. are preferred.

[0053] The unsaturated carboxylic acid or derivatives thereof used in the present invention include acrylic acid, methacrylic acid, maleic acid, fumaric acid, itaconic acid, citraconic acid or their anhydrides, metal salts and the like. Of these, maleic anhydride is preferred.

[0054] The free radical generator used for graft modification includes organic peroxides, dicumyl compounds, etc. Because of reactivity and ease of handling, organic peroxide-base compounds are preferred. Specific examples thereof include dicumyl peroxide, 2,5-dimethyl-2,5-bis(t-butylperoxy)hexane, 2,5-dimethyl-2,5-bis(t-butylperoxy)hexyne-3, 1,3-bis(2-t-butylperoxyisopropyl)benzene, benzoyl peroxide, etc. Examples of the dicumyl compounds include 2,3-dimethyl-2,3-diphenylbutane, 2,3-diethyl-2,3-diphenylbutane, 2,3-diethyl-2,3-di(p-methylphenyl)butane, 2,3-diethyl-2,3-di(p-bromophenyl)butane, etc. In particular, 2,3-diethyl-2,3-diphenylbutane is used preferably.

[0055] The hollow multilayer moldings of the present invention are obtained by extruding the respective resin layers described above through a multilayer die using a plurality of extruders and combine the layers before blow molding can be performed. For large vessels such as fuel tanks, drum cans and the like, drawdown resistance is more strictly required and fuel tanks are of complicated configuration since baffles are arranged therein so that local thinning tends to occur and hence puncture resistance, parison thickness controllability (parison control response), pinch-off shape properties, fire resistance and the like are required. In the present invention, use of the above-mentioned polymer or composition thereof of the present invention allows these requirements to be satisfied.

[0056] Further, in the present invention, it is desirable in view of economy to use, as an exterior layer of the hollow multilayer vessels, defective moldings of a laminate containing a layer of the above-mentioned (co)polymer of the present invention or composition thereof, an adhesive layer and a barrier layer, a recycled material such as burr, or a mixture of the recycled material, the (co)polymer of the present invention and general polyolefin resin. The blending amounts of the recycled material and polyolefin are not limited particularly.

[0057] The layer structure of the hollow multilayer vessels includes high density polyethylene (HDPE) layer of the invention/adhesive layer/polyamide resin (PA), HDPE layer of the invention/adhesive layer/EVOH, HDPE layer of the invention/adhesive layer/polyester resin (PET), HDPE layer of the invention/adhesive layer/PA/adhesive layer/HDPE layer of the invention, HDPE layer of the invention/adhesive layer/ethylene-vinyl acetate copolymer saponification product (EVOH)/adhesive layer/HDPE layer of the invention, HDPE layer of the invention/adhesive layer/PET/adhesive layer/HDPE layer of the invention, HDPE layer of the invention + HDPE/adhesive layer/PA/adhesive layer/HDPE layer of the invention, recycled layer/adhesive layer/PA/adhesive layer/recycled layer, recycled layer/adhesive layer/PA/adhesive layer/HDPE of the invention, recycled layer/adhesive layer/PA/adhesive layer/HDPE layer, recycled layer + HDPE/adhesive layer/PA/adhesive layer/HDPE layer, HDPE layer/adhesive layer/EVOH layer/adhesive layer/recycled layer/HDPE + carbon black layer, etc.

[0058] The thickness of respective layers of the hollow moldings is not limited particularly. In the case of multilayer moldings, generally the thickness of barrier layer is selected in the range of 0.001 to 1.0 mm, and preferably 0.01 to 0.5 mm, and the thickness of adhesive layer is selected in the range of 0.001 to 1.0 mm, and preferably 0.01 to 0.5 mm. Further, the thickness of the layer of the (co)polymer of the present invention or composition thereof and the thickness of other polyolefin layer are selected in the range of 0.5 to 10 mm, and preferably 1.0 to 7 mm.

BEST MODE FOR CARRYING OUT THE INVENTION

[0059] Hereafter, the present invention will be described in more detail by referring to examples and comparative examples. However, the present invention is not be limited to the following examples.

[0060] The physical properties of polyethylene and polyethylene resin compositions of Examples 1 to 3 and Comparative Examples 1 to 4, respectively, were measured by the following test method.

[Test Method]

(1) Density: According to JIS K6760.

(2) Flexural modulus: According to ASTM D790.

(3) HLMFR: According to JIS K6760.

(4) Measurement of molecular weight distribution:

[0061] Measurement was performed using 150 Type GPC manufactured by Waters and two columns, Shodex HT-806M, and 1,2,4-trichlorobenzene (TBC) containing 0.05% by weight of 2,6-di-*t*-butyl-4-methylphenol (BHT) as a solvent under the conditions of a sample amount of 0.8 mg/ml, a temperature of 140 °C, and a flow rate of 1 ml/min.

(5) Measurement of Die Swell:

[0062] "Capillograph 1C" manufactured by Toyo Seiko was used.

[0063] A sample molten at 230 °C was extruded through an orifice having a diameter of 1 mm, a length of 40 mm and an inlet angle of 90° in a region of shear rate ($\dot{\gamma}$) of 6.08 to 24.32 sec⁻¹ and the diameter of the strand at the time when the length of strand reached 75 mm was measured using a laser diameter measuring apparatus attached (distance between the outlet of capillary and die swell detector: 10 mm). Die swell ratio (DS) was calculated as D_s/D_o where D_s is the diameter of a strand and D_o is the diameter of an orifice. The slope a and intercept b were obtained by the method of least squares by the equation of relationship between DS and $\ln(\dot{\gamma})$:

$$DS = a \times \ln(\gamma) + b.$$

(6) Measurement of Stress Ratio

5 Preparation of Sample

[0064] "Capillograph 1C" manufactured by Toyo Seiko was used.

[0065] A sample molten at 210 °C was extruded through an orifice having a diameter of 3 mm, a length of 15 mm and an inlet angle of 90° at a constant piston speed of 10 mm/min to obtain a sample.

10

Measurement of Stress Ratio

[0066] "Melten Rheometer" manufactured by Toyo Seiki was used. After annealing at 170 °C for 1,000 seconds, a sample was clamped by a clamp and stretch viscosity measurement was practiced at a strain speed of 0.1 sec⁻¹. The stress at a strain of 1.0 was defined "σ1.0" and the maximum stress value generated until the sample was broken was defined "σmax" and stress ratio "σmax/σ1.0" was calculated.

15

Measurement of α Value and Time for Breakage

[0067] A sample obtained in the same manner as in the case of measurement of stress ratio were measured using "Melten Rheometer" manufactured by Toyo Seiki. That is, a sample was molten at 170 °C and then clamped by a clamp and its stretch viscosity was measured under a constant tension such that initial stress (= tension/initial cross section of sample) was 3.0x10⁴ Pa.

[0068] Assuming that when l_0 is an initial sample diameter and l_t is a sample diameter after t seconds, then $\epsilon = -\ln(l_t/l_0)$. The value of ϵ/t when $\epsilon=0.6$ is assumed to be α , and the time until a sample was broken was measured as a time for breakage.

25

(7) Extrusion Properties:

[0069] Multilayer blow molding machine "NB30" manufactured by Nippon Seikosho (main material extruder: 90 mm) was used and the extruded amount was measured at 60 rpm.

30

(8) Drawdown Resistance:

[0070] Multilayer blow molding machine "NB30" manufactured by Nippon Seikosho was used. A 1,600 cm-long parison weighing 8.5 kg was extruded at a resin temperature of 230 °C and after completion of the extrusion, changes in length of parison with lapse of time were measured. The parison after being shortened due to shrink back was sagging as a result of drawdown by self weight and elongated. The length of parison at the time when it was extruded is defined L_0 and the time counted from the that time until the parison once shortened by shrinking took the length of L_0 again was defined retention time, T_p , and evaluation of drawdown resistance was performed.

40

(9) Pinch-off Shape Properties

[0071] Using the above-mentioned blow molding machine and mold, 40-liter multilayer tanks (each weighing 6 kg) having a layer construction of resin layer of example or comparative example/adhesive layer (maleic anhydride-modified high density polyethylene)/nylon-6/adhesive layer/resin layer of example or comparative example were molded. The pinch-off portions of the obtained moldings were cut vertically with respect to pinch-off welded line. Pinch-off properties were evaluated from the thickness distribution in the cross sectional plane as shown in Fig. 1(a). The thickness of the welded portion at the pinch-off middle portion was defined "t" and the thickness of thicker portions on the both sides was defined "T", and pinch-off properties were evaluated by a ratio of t to T , t/T , (Fig. 1(b) and (c)).

50

(10) Puncture Resistance:

[0072] Using a multilayer blow molding machine "NB30" manufactured by Nippon Seikosho (screw diameter: 90 mm, die diameter: 120 mm) and molds having the same inlet size of $W1=200$, $W2=300$) and different depths D (100, 150, 200, and 250 mm), box-shaped hollow moldings were molded and deep draw ratio ($D/W1$) at which puncture of parison occurred was evaluated to thereby evaluate molding limit (puncture resistance).

55

(11) Tank Drop Test:

[0073] Using the above-mentioned multilayer tanks, drop tests were practiced. The drop tests were conducted by filling the tank with an aqueous 50% ethylene glycol solution to 70% of total volume and vertical drop tests were carried out at -40 °C at a height of 6 m.

(12) Parison Control Response

[0074] Using the above-mentioned blow molding machine and mold, box-shaped hollow moldings were obtained by setting a parison controller such that the thickness of a part of the middle portion of the molding was thickened at the time of molding. The parison controller used was a 25-point setting parison controller manufactured by MOOG, attached to the above-mentioned molding machine. By measuring the thickness distribution of the resultant hollow moldings, the controllability of parison controller for the thickness of a parison was measured. The thickness of the middle portion where the thickness was thickened was defined T_p and the thickness at standard point where no thickening occurred was defined T_s and a ratio T_p/T_s was calculated, which was used as an index of parison control response.

(13) Bottle Fire Resistance Tests:

[0075] Using the above-mentioned blow molding machine, 300 ml bottles having a thickness of 2 mm or 3 mm were molded. Water was poured into the resultant moldings up to 50% of the inner volume and the moldings were sealed. Then the moldings were burned with propane gas and the time until a hole opened was evaluated as fire resistant time.

(14) Press Plate Melting Test:

[0076] Press plates having a thickness of 2 mm or 3 mm were molded. The resultant press plates were burned from one side thereof with a mixed gas of methane and hydrogen and the time until the other side was molten was evaluated as melting time.

Example 1

[0077] Component 1 polymerized with a Phillips catalyst and Components 2 and 3 polymerized with $MgCl_2$ carried Ziegler catalyst were blended in a biaxial extruder (KTX-90 manufactured by Kobe Seikoshu) to prepare a sample of Example 1. The detailed data and blend ratio for each component are shown in Table 1. The measured properties data are shown in Table 6.

Table 1

Component	Blending proportion wt%	HL & MFR g/10min	Density g/cm ³
Component 1	70	HL=1.9	0.956
Component 2	10	HL=0.30	0.942
Component 3	20	MFR=800	0.970
Example 1	-	HL=2.3	0.955

Example 2

[0078] Component 1 polymerized with a Phillips catalyst and Components 2 and 3 polymerized with $MgCl_2$ carried Ziegler catalyst were blended in a biaxial extruder (KTX-90 manufactured by Kobe Seikoshu) to prepare a sample of Example 1. The detailed data and blend ratio for each component are shown in Table 2. The measured properties data are shown in Table 6.

Table 2

Component	Blending proportion wt%	HL & MFR g/10min	Density g/cm ³
Component 1	70	HL=1.9	0.956

Table 2 (continued)

Component	Blending proportion wt%	HL & MFR g/10min	Density g/cm ³
Component 2	10	HL=0.30	0.942
Component 3	20	MFR=800	0.970
Example 2	-	HL=3.1	0.957

Example 3

[0079] Component 1 polymerized with a Phillips catalyst and Components 2 and 3 polymerized with MgCl₂ carried Ziegler catalyst were blended in a biaxial extruder (KTX-90 manufactured by Kobe Seikoshō) to prepare a sample of Example 3. The detailed data and blend ratio for each component are shown in Table 3. The measured properties data are shown in Table 6.

Table 3

Component	Blending proportion wt%	HL & MFR g/10min	Density g/cm ³
Component 1	65	HL=1.9	0.956
Component 2	10	HL=0.30	0.942
Component 3	25	MFR=810	0.972
Example 3	-	HL=4.5	0.958

Comparative Example 1

[0080] Component 1 polymerized with a Phillips catalyst and Components 2 and 3 polymerized with MgCl₂ carried Ziegler catalyst were blended in a biaxial extruder (KTX-90 manufactured by Kobe Seikoshō) to prepare a sample of Comparative Example 1. The detailed data and blend ratio for each component are shown in Table 4. The measured properties data are shown in Table 6.

Table 4

Component	Blending proportion wt%	HL & MFR g/10min	Density g/cm ³
Component 1	70	HL=1.8	0.953
Component 2	10	HL=0.30	0.942
Component 3	20	MFR=790	0.968
Comparative Example 1	-	HL=3.0	0.954

Comparative Example 2

[0081] Component 1 polymerized with a Phillips catalyst and Components 2 polymerized with MgCl₂ carried Ziegler catalyst were blended in a biaxial extruder (KTX-90 manufactured by Kobe Seikoshō) to prepare a sample of Comparative Example 2. The detailed data and blend ratio for each component are shown in Table 5. The measured properties data are shown in Table 6.

Table 5

Component	Blending proportion wt%	HL & MFR g/10min	Density g/cm ³
Component 1	90	HL=1.9	0.956
Component 2	10	MFR=800	0.970

Table 5 (continued)

Component	Blending proportion wt%	HL & MFR g/10min	Density g/cm ³
Comparative Example 2	-	HL=4.2	0.957

5 Comparative Example 3

[0082] Using a commercially available high density polyethylene for blow molding (density = 0.947g/cm³, HLMFR = 4.6, JLex HD 4551H, manufactured by Japan Polyolefins Co., Ltd.) extrusion properties and the like were evaluated.
10 The results are shown in Table 6.

Comparative Example 4

[0083] Using a commercially available high density polyethylene for blow molding (density = 0.951g/cm³, HLMFR = 5.6, Hizex 8200B, manufactured by Mitsui Petrochemical Co., Ltd.) extrusion properties and the like were evaluated.
15 The results are shown in Table 6.

Table 6

ITEMS	Example 1	Example 2	Example 3	Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4
Density (g/cm ³)	0.955	0.957	0.958	0.954	0.957	0.947	0.951
Flexural modulus (Kg/cm ²)	—	15500	16000	14000	15200	11000	13000
HLMFR (g/10min)	2.3	3.1	4.5	3.0	4.2	4.6	5.6
Molecular weight distribution (Mw/Mn)	40	31	40	31	29	19	19
Die swell properties	0.029	0.030	0.033	0.032	0.084	0.036	0.029
Slope (a)	1.32	1.30	1.29	1.31	1.40	1.29	1.21
Intercept (b)	2.85	3.01	2.98	3.05	2.97	3.5	1.78
Stress ratio (σ max/ σ 1.0)	—	0.024	0.026	0.025	0.033	0.048	0.056
α Value	—	31.5	30.2	30.6	26	16.1	12.6
Time for breakage (second)	—	107	120	109	80	101	96
Extrusion properties (kg/hr)	101	>60	45	>60	35	30	18
Drawdown resistance (Γ p: second)	1.0	1.0	1.0	1.0	1.0	1.0	0.67
Pinch-off shape properties (Γ T)	>1.25	>1.25	>1.25	>1.25	>1.25	>1.25	1.0
Puncture resistance (Blow ratio:D/W1)	O	O	O	O	O	O	Pinch cracks
Tank drop test (-40 °C, 6m)	1.50	1.51	1.48	1.50	1.32	1.46	1.33
Parison control response (Γ p/ Γ s)	—	117	118	105	109	86	95
Bottle fire resistance test (hole opening time: second)	—	204	208	185	180	167	164
Press plate melting test (melting time: second)	—	32	36	27	31	21	24
	—	55	60	48	54	40	44

INDUSTRIAL APPLICABILITY

[0084] As described above, by use of the (co)polymer of the present invention there can be obtained hollow moldings which are excellent in drawdown resistance, puncture resistance, parison control response, pinch-off shape and fire resistance, causes no local thinning and is excellent in mechanical strength such as impact strength and rigidity. It can be used advantageously as a material for blow molding of large hollow moldings such as fuel tanks and drum cans having complicated shapes such as baffles.

Claims

10

1. An ethylene (co)polymer which satisfies the following requirements (a) to (d):

- (a) a density of 0.93 to 0.98 g/cm³,
 (b) a molecular weight distribution (Mw/Mn) of 25 to 50,
 (c) that values of slope a and of intercept b obtained from a die swell (DS) and a shear rate ($\dot{\gamma}$) measured in a region of shear rate ($\dot{\gamma}$) (6.06 to 24.8 sec⁻¹) at 230 °C, in accordance with the equation (1) below

$$DS = a \times \ln(\dot{\gamma}) + b \quad (1)$$

20

are such that $a \leq 0.05$ and $b \leq 1.45$,
 (d) that the stress ratio of a stress (σ) at a strain of 1.0 to a maximum stress (σ_{max}) in a stress-strain curve in uniaxial stretching at 0.1 sec⁻¹ measured at 170 °C is such that $\sigma_{max}/\sigma \geq 2.1$.

25 2. The ethylene (co)polymer as claimed in claim 1, wherein the ethylene (co)polymer further satisfies the requirement (e) that a value of (α) as defined by the equation (2) below

$$\alpha = \varepsilon/t \quad (2)$$

30 (wherein α is ε/t when ε defined by $\varepsilon = -\ln(\text{sample diameter after } t \text{ seconds } l_t / \text{initial sample diameter } l_0)$ is 0.6) when uniaxially stretched under a constant tension such that initial stress (= tension/initial cross section of sample) measured at 170 °C is 3.0×10^4 Pa is not greater than 0.03 and time for sample breakage is not shorter than 25 seconds.

35 3. The ethylene (co)polymer as claimed in claim 1 or 2, wherein the ethylene (co)polymer further satisfies the requirement (f) HLMFR ≤ 10 g/10 min.

4. The ethylene (co)polymer as claimed in any one of claims 1 to 3, wherein the ethylene (co)polymer has a C₃₋₂₀ α -olefin content of 10 mol% or less.

40 5. A hollow molding comprising the ethylene (co)polymer as claimed in any one of claims 1 to 4, or composition thereof.

6. The hollow molding as claimed in claim 4, wherein the hollow molding is a fuel tank.

45 7. A laminate comprising a layer comprising at least the ethylene (co)polymer as claimed in any one of claims 1 to 4 or compositions thereof and a barrier layer.

8. The laminate as claimed in claim 7, wherein the laminate comprises at least a layer of the ethylene (co)polymer as claimed in any one of claims 1 to 4 or compositions thereof, an adhesive layer, and a barrier layer.

50

9. The laminate as claimed in claim 7 or 8, wherein the barrier layer comprises at least one member selected from polyamide resins, ethylene/vinyl acetate copolymer saponification products, poly(meth)acrylonitrile resins, polyacetal resins, polyester resins, polyvinylidene chloride resins or compositions thereof.

55 10. The laminate as claimed in claim 8 or 9, wherein the adhesive layer comprises at least one adhesive resin selected from the group consisting of copolymers of unsaturated carboxylic acids or derivatives thereof with olefins and modified polyolefin resins grafted with unsaturated carboxylic acids or derivatives and mixtures of the adhesive resin with unmodified polyolefin.

11. A blow molded multilayer product comprising a laminate which comprises a layer comprising the ethylene (co)polymer as claimed in any one of claims 7 to 10 or compositions thereof, a barrier layer, and optionally an adhesive layer.

5 12. The blow molded multilayer product as claimed in claim 11, wherein the blow molded multilayer product is a fuel tank.

10 13. A blow molded multilayer product comprising a laminate which comprises a layer of at least one resin selected from recycled resins composed of the laminate as claimed in any one of claims 7 to 10, compositions of the recycled resins and the ethylene (co)polymer as claimed in any one of claims 1 to 3, or compositions of them with polyolefin resins, a barrier layer, and optionally an adhesive layer.

14. The blow molded multilayer product as claimed in claim 13, wherein the blow molded multilayer product is a fuel tank.

15

20

25

30

35


40

45


50

55

Fig. 1



(a)



(b)

(c)

INTERNATIONAL SEARCH REPORT

International application No.
PCT/JP98/02784

A. CLASSIFICATION OF SUBJECT MATTER Int.Cl. ⁶ C08L23/04, C08F10/02, B32B27/32 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) Int.Cl. ⁶ C08L23/00-23/36, C08F10/00-10/14, C08F110/00-110/14, C08F210/00-210/18 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP, 59-196346, A (Asahi Chemical Industry Co., Ltd.), 7 November, 1984 (07. 11. 84), Claims ; page 3, upper left column, line 3 to page 6, upper left column, line 15 (Family: none)	1-14
A	JP, 06-248124, A (Nippon Oil Co., Ltd.), 6 September, 1994 (06. 09. 94), Claims ; Par. Nos. [0004] to [0020] (Family: none)	1-14
EA	JP, 09-169087, A (Nippon Unicar K.K.), 30 June, 1997 (30. 06. 97), Claims ; Par. Nos. [0005] to [0021] (Family: none)	1-14
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search 24 August, 1998 (24. 08. 98)		Date of mailing of the international search report 8 September, 1998 (08. 09. 98)
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)